



# DESIGNED FOR DEXTERITY, COMFORT AND PROTECTION



## EXCEPTIONAL VALUE WITHOUT SACRIFICING COMFORT

### Safety & Protection

#### Infection Control

**Viral Penetration.** Although not an FDA requirement, Ansell's premium line of surgical gloves are tested to ensure protection against viral permeation. ENCORE® Perry® Style 42® PF has been tested and passed the viral penetration according to ASTM F1671-97a.

**Cuff Roll Down.** Inverted, beaded cuff to help prevent cuff roll down.

#### Skin Protection

**Low Protein Content.** This glove contains 50 µg/g or less of water/extractable protein per gram.

**Caution:** Safe use of these gloves by latex-sensitized individuals has not been established.

### Comfort & Fit

#### Donning

**Damp Hand Donnability.** Superb donning for a powder-free glove.

**Double Donnability.** This glove can be used as an under glove or an over glove depending upon the user's preference.

#### Hand Fatigue

**Shape of Glove/Former.** Anatomic curved former designed specifically by Ansell for a more natural fit and less hand fatigue.

**Stretchability (Modulus).** Modulus refers to glove comfort on the hand in a stretched state. Latex has a modulus that provides great comfort without it being baggy or tight.

#### Tactile Sensitivity

**Dependability.** The thickness of these gloves is optimized for the best balance of protection and tactile sensitivity, all while allowing for a comfortable fit during the majority of surgical procedures.

#### Grip

**Application Driven.** Anti-slip smooth finish for a comfortable, secure grip.



**Product**  
**Material**  
**Packaging**

ENCORE® Perry Style 42® Powder-Free Sterile Surgical Gloves  
Natural rubber latex in compliance with ASTM D 1076  
1 Sterile Pair/Polyethylene Package — 50 Pairs/Dispenser Box — 4 Boxes/Case

**Product Numbers**

**Dimensional Specifications**

Size	Catalog #	Minimum Length mm (inches)	Average Palm Width mm (inches)
5 ½	5711100PF	278 (10.9)	72 (2.8)
6	5711101PF	280 (11)	77 (3.0)
6 ½	5711102PF	280 (11)	83 (3.3)
7	5711103PF	283 (11.1)	89 (3.5)
7 ½	5711104PF	287 (11.3)	95 (3.7)
8	5711105PF	288 (11.3)	102 (4.0)
8 ½	5711106PF	290 (11.4)	108 (4.3)
9	5711107PF	290 (11.4)	114 (4.5)

**Thickness (single)**

Data from sampling	Average Thickness	Range
Fingertip mm (mils)	0.21 (8.3)	± 0.03 (1.2)
Palm mm (mils)	0.17 (6.7)	± 0.03 (1.2)
Cuff mm (mils)	0.15 (5.9)	± 0.02 (0.8)

**Physical Properties (ASTM Requirements)**

	Before Aging	After Aging
Tensile Strength (MPa)	Min. 24	Min. 18
Elongation (%)	Min. 750	Min. 560
Modulus 500% (MPa)	5.5	N/A
Force at Break (N)	Min. 12	Min. 9

Manufacturing specifications meet or exceed all the above.

<b>Color</b>	White
<b>Accelerators</b>	Zinc dibutyldithiocarbamate (ZDBC) Zinc diethyldithiocarbamate (ZDEC)
<b>Powder-Free</b>	Eliminates powder-related post-operative complications and sensitivity
<b>Certification</b>	Manufacturing Facility Registered to ISO 9001 and 13485 (The latter supersedes EN 46001) Contains 50 micrograms or less of total water-extractable protein per gram
<b>Quality Control</b>	In compliance with ASTM D 3577-00, Type I
<b>Sterilization</b>	Gamma radiation; Sterility Assurance Level (SAL) 1/1,000,000
<b>References</b>	ANSI/ASQC Z1.4 Sampling Procedures and Tables for Inspection by Attributes
<b>Storage</b>	Cool environment, shielded from ozone and UV light
<b>Dispenser</b>	16.0 x 13.2 x 28.2 inches

CAUTION: This product contains natural rubber latex which may cause allergic reactions, including anaphylactic responses.

\*Acceptable Quality Level

Except for applicable ASTM requirements, the above information represents typical data for the product and should not be construed or used as an actual product performance specification.

**For information and samples, call Ansell  
at 800-952-9916, or visit us at [www.ansell.com](http://www.ansell.com)**

Ansell Healthcare Products LLC  
111 Wood Avenue South, Suite 210, Iselin, NJ 08830 U.S.A Tel.: 800 952-9916

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates.  
© 2016 Ansell Limited. All Rights Reserved.  
[www.ansell.com](http://www.ansell.com)